

## **Technical Data Sheet**

## POLYPROPYLENE FIBERS 50µm Monofilament Product Code Prefix: PPSTM-050NRR

General Decription: Polypropylene is a manufactured fiber in which the fiber-forming

substance is a long-chain synthetic polymer composed of at least 85% by weight of propylene units. This  $50\mu m$  monofilament is a very fine fiber that is specially suited to reduce shrinkage and prevent crack

formation in cementitious materials.

Standard Filament Size: 50µm

Standard Cut Lengths: 3mm, 6mm, 12mm, 18mm

Tensile Strength: ≥152 MPa Elastic Modulus: ≥1.1 GPa Specific Gravity: 0.91 g/cm³

**Average Moisture Absorption: <0.1%** 

Effects of Heat: Softens at ~160°C /~320°F. Melts at ~168°C /~335°F.

Decomposes at ~288°C /~550°F.

In concrete, with the development of intense heat, the fibers will melt and create small capillary cavities, which can delay explosive

fragmentation.

Chemical Resistance: Good resistance to acids and alkalis. Physically resistant to chemicals

in concrete.

Performance Characteristics: This fiber is specially treated to reduce air intake in cementitious

products, which decreases porosity and improves strength. It has high dispersibility in the matrix, and the fineness of the fibers results in a high fiber frequency and increased surface area. This provides increased tensile strength and helps to evenly distribute early

shrinkage tension, thus reducing the formation of cracks and long-term weaknesses in the material. The 50µm product is especially well suited

for use in dry mixes.

Other Characteristics: One of the lightest of all fibers. Not attacked by microorganisms, mold

or mildew. Low thermal conductivity. Very little tendency to aguire

static charge.

**Packaging:** Standard packaging is corrugated boxes with polyethylene liners.

Other packaging available upon request.

The above information is provided to describe typical values and does not constitute a product specification. MiniFIBERS warrants that for each Product sold, such Product will meet the standard specifications provided for that Product and will be of a quality consistent with the standard specifications. This is the sole warranty given with respect to the Product, and is given expressly in lieu of any other warranties, expressed or implied, including without limitation any implied or general warranty of merchantability or of fitness for a particular purpose. It is expressly understood that any technical advice or assistance that may be provided by MiniFIBERS is rendered without compensation, and MiniFIBERS assumes no obligation or liability for such advice or assistance given, or for results obtained.

Doc: PI-TDS\_Polypropylene-for-Dry-Mix\_50um DCN 200801